

19544451DE

USPTO 2003-5645

Translated from the GermanFEDERAL REPUBLIC OF GERMANY
GERMAN PATENT OFFICE**Offenlegungsschrift**
DE 195 44 451 A 1IPC: B 32 B 27/32
B 32 B 5/28
B 32 B 5/18
B 32 B 27/04
E 04 C 2/24
//B32B 17/04, B60R 13/08Date of application: November 29, 1995
Date the 'offenlegungsschrift' was laid open to public
inspection: June 5, 1997

Applicant: BASF A.G., D-67063 Ludwigshafen
Inventor: Claus Molitor, D-68307, and Dieter Urban D-55278
Uelversheim
Title in German of the object of the invention:
Sandwichplatten

SANDWICH PANELS

Description

The invention pertains to sandwich panels [*Translator's note:
Also known as laminated panels] of a polypropylene-foamed core layer
and cover layers of glass-fiber matting reinforced polypropylene*
[*Translator's note: Also known as PP, and Propathene7 (i.e. the polypropylene
homo- and copolymers)].

For many a great number of applications, there is a requirement to light structural elements, which - besides a low weight and a low price - should have a very adequate strength and stiffness (rigidity), and, moreover, be easily recyclable.

These requirements are met by the sandwich panels in accordance with the invention. These sandwich panels consist of:

A - A core layer of polypropylene particle foam, having a density of 0.02 to 0.10 g.cm³ [sic!!!] [*Translator's note: Presumably, and, most probably, the inventors have in mind, 0.02 to 0.10 g/cm³ rather than 0.02 to 0.10 g.cm³ but have not been able to express this explicitly, and have left it to the imagination of the readers.]

B - Two cover layers of glass-fiber matting reinforced polypropylene, having a fiber content of 20 to 60 % by weight.

The core layer A consists of a particle foamed material [*Translator's note: Also known as expanded (foamed; aerated cellular) plastic; cellular polymer; plastic foam] on the basis of a homopolymers or copolymers of the polypropylene. Preferably, propylene copolymers are used, having a melting point between 125 and 155°C, preferably between 130 and 150°C. In doing so, the maximum value, defined in accordance with the DSC-method* [*Translator's note: The inventors have not specified what the abbreviation or acronym DSC mean. It could mean either a) thin-layer chromatography; or b) differential scanning calorimetry, which is used in thermoanalysis.] over the course of the second melting of a sample (crystallite melting point), holds true in its capacity as melting point. Copolymers

of the propylene, having 1 to 30 % by weight, in particular 1 to 6 % by weight of ethylene, and/or of a C₄-to C₆ - α -olefin, are especially suitable in an efficient way.

The foamed material is a so-called particle foamed material, as it can be obtained by hot sealing [thermal sealing] of foamed-material particles, customarily having a mean diameter of 2 to 8 mm, preferably 3 to 6 mm. The density of the foamed material is between 0.03 and 0.08 g/cm³.

Preferably, the thickness of the core layer constitutes 5 to 100, in particular 5 to 40 mm.

The cover(ing) layers B consist of glass-fiber matting reinforced polypropylene. This contains 20 to 60, preferably 30 to 45 % by weight of glass fibers, preferably in the form of mats [mattings]. The mattings bring about the high strength of the material. The length of the glass fibers can vary in wide ranges, between approximately 2 mm and infinity. Preferred are mats, which consist of cut [sic] glass-fiber rovings*, having a length of 5 to 25 mm, [*Translator's note:

The word rovings implies glass-fiber rovings. However, roving implies untwisted glass fiber, which is already c u t. Also known as rowing, i.e. untwisted thread/strand between sliver and strand], and which were needle-punched. Over the course of the needle-punching, several glass-fibers were shattered, or broken to pieces, so that the needle-punched mat also has contents of shorter fibers.

Preferably, the gram weight [basis weight] of the glass-

fiber mats constitutes 200 to 1,200 g/m². The cover layers are preferably having a thickness of 1 to 10, in particular 2 to 5 mm.

The manufacturing of the sandwich panels in accordance with the invention takes functionally place as a result of the compaction or molding of cover layers, which have been preheated to a temperature range of about 210 °C, with the core layer. Basically, however, the layers can also be glued to one another.

For example, the laminated composites* [*Translator's note: Also known as laminated sheet materials] can also be used as sound-insulating materials in the construction industry, or as automobile parts, e.g., loading (cargo) floors or bottoms, heat-insulating elements, or sound-absorbing structural components.

Patent Claims

1. Sandwich panels (plates), consisting of

A - A core layer of polypropylene particle foam, having a density of 0.02 to 0.10 g.cm³ [sic !!!]

B - Two cover layers of glass-fiber matting reinforced polypropylene, having a fiber content of 20 to 60 % by weight.

2. Sandwich panels (plates) as claimed in claim 1, characterized in that the core layer A has a thickness from 5 to 100 mm, and the cover layer has a thickness of 1 to 10 mm.

USDoC/US PATENT & TRADEMARK OFFICE/STIC/Translations Branch
Translated by Dipl.-Ing. John M Koytcheff, MSc (Engrg.); WHO
Fellow (Engrg.)
USPTO Translator (GERMAN)
September 24, 2003